# Super-Adhesive Filler 945

Technical information sheet

/ Item no.003904208 / EAN 4016215105016
/ Item no.003908208 / EAN 4016215105030




Ideal for smoothing entire surfaces, sealing joints in filigree and precast ceilings, filling cracks and holes, and jointing plasterboard, gypsum fibreboard, cement fibreboard and similar drywall panels. Tension-free drywall panels can be filled without the need for reinforcement tape. Please follow the panel manufacturers' application instructions. The profimur Super-Haftspachtel offers excellent adhesion to the substrate, filling power and stability. It is vapour-permeable and provides an ideal substrate for subsequent wallpapering and painting work. Thanks to its smooth consistency, the profimur Super Adhesive Filler is ideal for creating smooth or textured surfaces. Not suitable for use in areas directly exposed to splashing water, such as wet rooms, showers, swimming pools, saltwater baths, commercial kitchens and similar, nor for filling on glass, plastic, wood, metal and emulsion-based substrates.

- Painting and plasterboard filling spatula
- Ideal for smoothing the entire surface and for jointing tension-free plasterboard and gypsum fibreboard, even without reinforcement tape
- for all plasterboard systems in accordance with EN 13963
- synthetic resin-coated and fibre-reinforced
- Extendable to zero for seamless surfaces
- for surface grades Q1 – Q4 in drywall construction (in accordance with Technical Note No. 2 of the Plasterboard Industry Group within the Federal Association of the Plaster and Plasterboard Industry (Bundesverband der Gips- und Gipsbauplattenindustrie e.V.))
- for indoors
- 45 minutes' processing time
- CE-compliant in accordance with DIN EN 13963-4B and DIN EN 13279-1 (gypsum surface filler C7/20/2)

## Area of application

A synthetic resin-reinforced gypsum filler with excellent adhesion properties for interior walls and ceilings.

## Preparation

Suitable for use on all mineral substrates (such as gypsum, lime and cement plaster, stone, concrete, aerated concrete, masonry and the like) as well as on plasterboard, gypsum fibreboard, cement fibreboard and similar drywall panels. The substrate must be dry, sound and free from release agents (dust, formwork oil, etc.). Pre-treat very smooth concrete as well as highly absorbent, sandy and chalky substrates with profimur Deep Primer LF. Sanded surfaces and the cut edges of plasterboard must also be primed to bind dust and reduce absorbency.

## Processing

Preparation:
Add 2 parts profimur Super-Haftspachtel to 1 part cold, clean water (e.g. 1 kg of powder to 600 ml of water) and mix. After 3 minutes, give the filler a quick stir again.

Application:
Apply the mixed filler within 45 minutes using a filling knife or trowel and smooth it to a flush finish. The profimur Super-Haftspachtel can also be applied in thicker layers in a single pass and hardens evenly without sagging or cracking. Depending on the application thickness, ambient conditions and building moisture content, the drying time is approx. 24 hours – under unfavourable conditions, the drying time may be extended accordingly.



Baufan Bauchemie Leipzig GmbH ■ Ludwig-Hupfeld-Straße 19 ■ 04178 Leipzig ■ Telephone +49 (0)341 44655-0 ■ Email info@baufan.de ■ www.baufan.com

**Note:**
All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.

Practical tip: Sanding:
The filled surfaces are easiest to sand within 4 days of application. For optimum sanding results, we recommend using a disc sander (120-grit sandpaper) at slow to medium speeds and with light pressure.

Follow-up work:
To prevent subsequent coats from drying unevenly when spot-filling, the repaired areas – or even the entire surface – should be primed with profimur Tiefengrund LF.

## Consumption
Approx. 1 kg of powder per m² at an application thickness of 1 mm.

## Storage
Keep out of the reach of children, in a cool, dry place. Keep opened containers tightly closed.

## Notes
Do not apply when the object or ambient temperature is below +5 °C. Clean tools with water after use.

Please refer to the safety data sheet for safety-related information. Up-to-date safety data sheets are available on our website www.baufan.de or at info@baufan.de.

Only send completely empty containers for recycling. Dried-out material residues may be disposed of as household waste or as construction site waste. EWC waste code no. 17 08 02. Do not allow the product to enter the mains drainage system, watercourses or the ground.



Baufan Bauchemie Leipzig GmbH ■ Ludwig-Hupfeld-Straße 19 ■ 04178 Leipzig ■ Telephone +49 (0)341 44655-0 ■ Email info@baufan.de ■ www.baufan.com

**Note:**
All details and data presented in this information sheet are based on our practical experience and laboratory investigations, and reflect the current state of the art. They can, however, only serve as general guidance and shall provide no guarantee of specific properties or performance. Given that the conditions for storage, transportation and application of products are beyond our control, no legal liability may be construed from the information presented here. It shall be the responsibility of the user to check the product's suitability for the envisaged purpose under the specific site or project conditions.